FOREST BRIGHT
ARCHITECTURAL WOOD DOOR

PAINT GRADE AGRIFIBER CORE FLUSH WOOD DOOR

NON-RATED & 20 MINUTE POSITIVE PRESSURE

Models	AG-PR-00 AG-PR-20			
Maximum Size	ITS-WH MAX 20min, 1-3/4" or 2" thick			
		Non-Rated	CAT A Positive Pressure	CAT B Positive Pressure
	Single	4'0"x10'0"	4'0"x8'0"	4'0"x8'0"
	Pairs	8'0"x10'0"	8'0"x8'0"	8'0"x8'0"
Faces	Primed High Density Fiberboard (HDF) or Medium Density Overlay (MDO).			
Core	Agrifiber core.			
Weight	Approx. 5.5 lbs. per square foot (1-3/4").			
Vertical Stiles	1-3/8" SCL stiles.			
Top Rail	1-3/8" SCL top rail.			
Bottom Rail	1-3/8" SCL bottom rail.			
Factory Finish	Factory primed or factory opaque finish to meet WDMA OP-6.			
Machining	All hardware preparations, including pre-drilled hinge pilot holes and mortise cutouts, are factory-machined strictly per approved shop drawings and manufacturer templates.			
Cutouts	5-1/2" minimum distance from door edge and the minimum distance between lite and lock cut out is 3-1/4" for 20-min fire door.			
Bevel Option	Non-bevel, 1 side bevel or 2 side bevels, 1/8" at 2" as standard.			
Quality Standard	ANSI/WDMA I.S.1-A standard; AWS Section 9 & bonded core available on request.			
WDMA Performance Level	Heavy Duty. Blocking required for face-applied hardware at extra heavy duty.			
Warranty	Limited Lifetime, Interior use only.			
Cross Section				



Note: Doors are manufactured per the standards listed on this page. Specifications are subject to change without notice.
** Fire-Rated doors will be constructed per label service listing and may deviate from above.*

info@forestbright.com
www.forestbright.com