FOREST BRIGHT
ARCHITECTURAL WOOD DOOR

WOOD VENEER AGRIFIBER CORE FLUSH WOOD DOOR

NON-RATED & 20 MINUTE POSITIVE PRESSURE

Models	AG-V-00 AG-V-20			
Maximum Size	ITS-WH MAX 20min, 1-3/4" or 2" thick			
		Non-Rated	CAT A Positive Pressure	CAT B Positive Pressure
	Single	4'0"x10'0"	4'0"x8'0"	4'0"x8'0"
	Pairs	8'0"x10'0"	8'0"x8'0"	8'0"x8'0"
Faces	WDMA custom "A" grade wood veneer as standard. Premium"AA" grade available by request. Different species of natural wood veneer available, reconstituted wood veneer available.			
Crossbands	High Density Fiberboard (HDF).			
Core	Agrifiber core.			
Weight	Approx. 5.5 lbs. per square foot (1-3/4").			
Vertical Stiles	1-3/8" SCL stiles with matching hardwood edge or veneer edgebanding.			
Top Rail	1-3/8" SCL top rail with matching hardwood edge or veneer edgebanding.			
Bottom Rail	1-3/8" SCL bottom rail.			
Factory Finish	WDMA TR-6 Catalyzed Polyurethane factory finish to match custom color sample.			
Machining	All hardware preparations, including pre-drilled hinge pilot holes and mortise cutouts, are factory-machined strictly per approved shop drawings and manufacturer templates.			
Cutouts	5-1/2" minimum distance from door edge and the minimum distance between lite and lock cut out is 3-1/4" for 20-min fire door.			
Bevel Option	Non-bevel, 1 side bevel or 2 side bevels, 1/8" at 2" as standard.			
Quality Standard	ANSI/WDMA I.S.1-A standard; AWS Section 9 & bonded core available on request.			
WDMA Performance Level	Heavy Duty. Blocking required for face-applied hardware at extra heavy duty.			
Warranty	Limited Lifetime, Interior use only.			
Cross Section				



Note: Doors are manufactured per the standards listed on this page. Specifications are subject to change without notice.
** Fire-Rated doors will be constructed per label service listing and may deviate from above.*

info@forestbright.com
www.forestbright.com